

Characteristics

PC / Nove - SK is a porcelain body.
Available as spray - dried granulate.

Firing Colour	white - light grey
Recommended Firing Temperature Range	1200 - 1240 °C


Technical Data

Unfired

Moisture	6,5% spray dried							
Chemical Analysis	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	K ₂ O	Na ₂ O
	64,8%	0,10%	28,0%	0,50%	0,60%	0,20%	2,90%	2,90%
Loss of Ignition	6,8%							
Wet to Dry Shrinkage	2,8% casting							

Fired

Specimen Firing Temperature [°C]	1200	1240
Coefficient of Thermal Expansion [x10 ⁻⁶ /°C]		
20 - 400 °C	6,0	5,7
20 - 500 °C	6,2	5,9
20 - 600 °C	6,6	6,1
Dry to Fired Shrinkage [%]	11,0	10,5
Water Absorption [%]	0,0	0,0



Gießfix 162	
Optimum Amounts	0,0 - 0,02%

First deflocculant and afterwards, add the granulate under slow stirring to the water.

Specific Weight to Achieve	1740 - 1760 g / l
----------------------------	-------------------

PC / Nove - SK needs about 38 l water per 100 kg to achieve s.w. of 1740 g / l.

Test the casting advice in own production first remembering the mentioned amounts are depending on the hardness of the water, the type of blunger, and the desired properties of the casting.

- use the right amount of deflocculant to achieve optimum casting time
- if castthickness is too small, use less deflocculant
- don't use more than 10 - 15 % of scrap (above the fresh made slip)

The technical data quoted on this sheet is indicative only. Any sale is by sample and is governed by our general conditions of sale.



Sibelco Deutschland GmbH
Sälzerstraße 20
56235 Ransbach-Baumbach
DEUTSCHLAND

Tel.: +49 2623 8828-0
Fax: +49 2623 8828-92
E-Mail: kontakt@sibelco.de

24.11.2016